

Product Information

HEX-FLEX® RAPID is our newest polyurethane transfer film equipped with a special hotmelt for fast application at low temperature.

HEX-FLEX® RAPID is suitable for transfer to textiles like cotton, polyester, uncoated nylon, mixtures of polyester/cotton and polyester/acrylic. For application to Nylon that is treated with any kind of coating, please test for suitability. HEX-FLEX® RAPID can be used for lettering on T-shirts, sport & leisure wear, sport bags and promotional articles.

HEX-FLEX® RAPID can be cut with all current plotters. We recommend using a standard 45° knife. After weeding the cut flex film is transferred by heat press. The polyester liner should be removed warm, except for the neon colours (4903, 4940 – 4943) the liner should be removed lukewarm.

The soft, elastic transfer film offers a comfortable textile touch and convinces due to high wearing comfort. HEX-FLEX® RAPID excels due to an excellent opacity. HEX-FLEX® RAPID with a self-adhesive PET liner enables a reposition. The raw materials are ecologically inert, do not contain PVC, plasticizers or heavy metals (in accordance with Oeko-Tex Standard 100 Class I).

Guarantee for a secure and long-lasting bond of HEX-FLEX® PREMIUM is only given when following the specified temperature and pressure conditions.

With the exception of 4920 Gold Metallic, 4930 Silver Metallic and the Neon colours (4903, 4940 – 4943), the HEX-FLEX® RAPID series can be pressed on top of each other.

We recommend evaluation on test material.

Due to the various influences which occur from production and transfer of plotter letterings, consistency of the carrier materials and also washing and cleaning conditions, product liability can only cover the unprocessed material.

Standard Dimensions

500 mm x 10 m *
500 mm x 25 m
1.000 mm x 25 m *
1.524 mm x 25 m *

*Non-standard dimension. Converted after order entry. Extended delivery times may occur

Technical Data

Transfer Film: Polyurethane, cast
Thickness [mm]: 0,095 +/- 5 %
Liner: PET-film, self-adhesive

Transfer Conditions

Pressure: 2,5 - 3,0 bar [medium pressure]
Temperature / Time: 130 °C, 5 sec. / 150 °C, 4 sec. / 160 °C, 3 sec.

NYLON

Pressure: 2,0 bar [low pressure]
Temperature / Time: 150 °C,
• Pre Heat 5 sec.
• Apply to Nylon 5 sec.
• Remove PET liner, cover transfer with silicon paper & apply for further 10 sec.

Please consider to adjust the application time when using highly structured cotton or cotton mixture fabrics.

Wash Resistance

Wash resistance: 60 °C
Suitable for tumble drying (commercial tumble dryer up to 100°C) and dry-cleaning.
Wash textile inside out.

Safety Data Sheet

When used under normal conditions, this product does not generate or release any dangerous substances or hazardous chemicals. This is a non-hazardous product in accordance with the current GefStoffV and EU criteria. Therefore it is not necessary to prepare a Material Safety Data Sheet for this product. The Safety Data Sheet serves only to comply with the regulation to supply information in accordance with REACH Regulation (EC) No. 1907/2006 and is available on request. This product is not a hazardous product with regards to transportation legislation; neither does it contain substances that are hazardous to water within the meaning of the federal water act. After use, dispose of the waste product in accordance with the local / national authorities.